



INDUSTRIAL METAL

Product	Chemistry	Substrate	VOC Formulation Capability - g/L	Application				Properties			Performance Benefits
				Corrosion Resistance	Block Resistance	Early Water Resistance	Chemical Resistance	Solids (%)	pH	MFFT (°C)	
EPS® 2580	Styrenated Acrylic	CRS Aluminum Galvanized substrates	<50	✓	✓	✓	●	48	8.5-9.0	8-12	• Early hardness development • Early hot block resistance • Adhesion to ferrous and non-ferrous metals • Corrosion and chemical resistance
EPS® 2585	Styrenated Acrylic	CRS Aluminum Galvanized substrates	<100	✓	✓	✓	●	50	8.5-9.5	18-24	• Hardness and block resistance at low VOC • Corrosion resistance without the use of anticorrosive pigments • Early water resistance
EPS® 2561	Styrenated Acrylic	Metal (2k applications) Plastic	<100	✓	✓	●	✓	37	6.5-7.3	-	• Hydroxyl functional • Corrosion resistance • Adhesion to ferrous and non-ferrous metal substrates, including brass • Lower temperature cure response – as low as 225°F
EPS® 2513	Styrenated Acrylic	CRS Aluminum Galvanized substrates	<100	✓	●	✓	●	50	8.0-9.0	23	• Corrosion resistance without the use of anticorrosive pigments and additives • High gloss development and good gloss retention • Early water resistance, including water immersion • Adhesion to ferrous and non-ferrous metal substrates
EPS® 2574	Styrenated Acrylic	Metal Wood Cementitious Plastic	<200	●	✓	✓	●	50	8.0-9.0	53	• Hardness development • Block, print and stain resistance • Early water resistance • Multi-substrate adhesion

✓ Leading Performance

● Competitive Performance



INDUSTRIAL METAL

Product	Chemistry	Substrate	VOC Formulation Capability - g/L	Application				Properties			Performance Benefits
				Corrosion Resistance	Block Resistance	Early Water Resistance	Chemical Resistance	Solids (%)	pH	MFFT (°C)	
EPS® 2559	Styrenated Acrylic	Metal Wood Cementitious Plastic	<200	●	✓	✓	●	50	7.0-8.0	44	• High gloss • Corrosion resistance • Early water and humidity resistance • Block, mar and print resistance
EPS® 2540	Styrenated Acrylic	Metal Wood Plastic	<200	✓	●	●	●	50	7.5-8.5	57	• Corrosion resistance without the use of anticorrosive pigments and additives • Gloss development and retention • Adhesion to ferrous and non-ferrous metal substrates • Early water resistance and broad solvent compatibility

✓ Leading Performance

● Competitive Performance

THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.

CONTACT INFORMATION

EPS Headquarters
1400 N. State St.
Marengo, Illinois 60152

Sales and Customer Service
Phone: 800-654-4242
Email: info@epscsa.com

EPS Technical Service
Phone: 800-654-4242
Email: info@eps-materials.com

epscsa.com