



SPECIALTY

Product	Chemistry	Application				Properties			Performance Benefits
		Arts & Crafts	Graphic Arts	Nonwovens & Textiles	Specialty Products	Solids (%)	pH	MIFFT (°C)	
EPS® 2574	Styrenated Acrylic	●				50	8.0-9.0	53	• Rapid block resistance • Hardness • Stain resistance
EPS® 2775	All-Acrylic	●				50	8.5-9.0	12.5	• Ideal for lower sheen or low VOC formulations • Yellowing and UV resistance • Multi-substrate adhesion • No intentionally added fluorosurfactants or APEO surfactants • Capable of meeting ACMI approval
EPS® 2785	All-Acrylic	●				50	8.5-9.0	18.5	• Ideal for higher sheen or extended open time formulations • Yellowing and UV resistance • Glass adhesion • No intentionally added fluorosurfactants or APEO surfactants • Capable of meeting ACMI approval
RayRez® 66	Styrenated Acrylic		●			46	9.0-9.5	30	• Ideal for flexographic and rotogravure printing inks • Rub resistance • High gloss and transparency • Resolubility • Ink transfer
EPS® 2512	Styrenated Acrylic			●		45	7.0 - 8.0	18	• Air and moisture barrier performance • Early water resistance and hydrophobicity • Compatible with highly filled formulations • Stable under elevated temperature conditions
RayCryl® 1837	All-Acrylic			●		50	3.0-4.5	41	• Self-crosslinking and carboxyl group • Hard and stiff all-acrylic emulsion • Accepts high filter loading and flame retardants
RayCryl® 1856	All-Acrylic			●		55	3.0-4.5	23	• Self-crosslinking and carboxyl group • Excellent foamer • Compatible with fillers such as clay, starch or calcium carbonate



SPECIALTY

Product	Chemistry	Application				Properties		pH	MFFT (°C)	Performance Benefits
		Arts & Crafts	Graphic Arts	Nonwovens & Textiles	Specialty Products	Solids (%)				
RayCryl® 1859	All-Acrylic			•		55	3.0-4.5	0		• Self-crosslinking and carboxyl group • Medium flexible film • Compatible with clay, starch or calcium carbonate • Outstanding UV resistance and film clarity
EPS® 9147	Low-VOC Coalescent				•	>99.1	-	-	-	

THE EXPERTISE BEHIND THE INNOVATION

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. Unless otherwise agreed in writing, all sales of EPS products are governed by the EPS Terms and Conditions of Sale, available at <https://www.epscsa.com/galleries/pdfs/salesterms.pdf>.

CONTACT INFORMATION

EPS Headquarters
1400 N. State St.
Marengo, Illinois 60152

Sales and Customer Service
Phone: 800-654-4242
Email: info@epscsa.com

EPS Technical Service
Phone: 800-654-4242
Email: info@eps-materials.com